

TSE Industries Millathane® 76 Millable Polyester Polyurethane Rubber, 2.0 PHR Di-Cup 40C Peroxide

Category : Polymer , Thermoset , Polyester, TS , Polyurethane, TS , Thermoset Polyurethane, Elastomer, Unreinforced , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Millathane® 76 is a very suitable choice for use in products such as bushings, small copier rolls; automotive applications – bumpers, o-rings, hydraulic seals, belts, gaskets, solid tires – and many other high performance polyurethane applications. Millathane 76 can be vulcanized by sulfur or peroxide cured systems. Curing of Millathane®76 can easily be done with many types of peroxides. Millathane76 peroxide vulcanizates have superior compression set, greater heat stability, and are more resistant to reversion than sulfur cures. Formulation Millathane 76 100.0Stearic Acid 0.5N-220 Black20.0Di-Cup 40C 2.0All information provided by TSE Industries

Order this product through the following link:

http://www.lookpolymers.com/polymer_TSE-Industries-Millathane-76-Millable-Polyester-Polyurethane-Rubber-20-PHR-Di-Cup-40C-Peroxide.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	60	60	
Tensile Strength, Yield	28.55 MPa	4141 psi	
Elongation at Yield	475 %	475 %	
100% Modulus	0.00192 GPa	0.278 ksi	
200% Modulus	0.00527 GPa	0.764 ksi	
300% Modulus	0.01211 GPa	1.757 ksi	
Tear Strength	58.7 kN/m	335 pli	Die C
Compression Set	29 %	29 %	
	@Temperature 100 °C, Time 79200 sec	@Temperature 212 °F, Time 22.0 hour	

Processing Properties	Metric	English	Comments
Cure Time	15.0 min	0.250 hour	
	@Temperature 160 °C	@Temperature 320 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China