

## TSE Industries Millathane® 76 Millable Polyester Polyurethane Rubber, 40 PHR Carbon Black, N-326 (HS-HAF)

Category : Polymer , Thermoset , Polyester, TS , Polyurethane, TS , Thermoset Polyurethane, Elastomer, Unreinforced , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

Millathane® 76 is a very suitable choice for use in products such as bushings, small copier rolls; automotive applications – bumpers, o-rings, hydraulic seals, belts, gaskets, solid tires – and many other high performance polyurethane applications. Millathane 76 can be vulcanized by sulfur or peroxide cured systems. Formulation Millathane 76 100.0Zinc Stearate0.5Poly AC 617A1.0TP-9510.0Thanecure® ZM1.0MBTS4.0MBT2.0Sulfur1.5N-32640All information provided by TSE Industries

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_TSE-Industries-Millathane-76-Millable-Polyester-Polyurethane-Rubber-40-PHR-Carbon-Black-N-326-HS-HAF.php](http://www.lookpolymers.com/polymer_TSE-Industries-Millathane-76-Millable-Polyester-Polyurethane-Rubber-40-PHR-Carbon-Black-N-326-HS-HAF.php)

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	74	74	
Tensile Strength, Yield	25.8 MPa	3740 psi	
Elongation at Yield	569 %	569 %	
100% Modulus	0.00412 GPa	0.598 ksi	
200% Modulus	0.008108 GPa	1.176 ksi	
300% Modulus	0.01257 GPa	1.823 ksi	
Tear Strength	69.0 kN/m	394 pli	
Taber Abrasion, mg/1000 Cycles	8.0 @Load 1.00 kg	8.0 @Load 2.20 lb	H-18 wheel
Compression Set	59.2 % @Temperature 70.0 °C, Time 79200 sec	59.2 % @Temperature 158 °F, Time 22.0 hour	

Processing Properties	Metric	English	Comments
Cure Time	11.0 min @Temperature 154 °C	0.183 hour @Temperature 309 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China