

## TSE Industries Millathane® 76 Millable Polyester Polyurethane Rubber, 4.0 PHR Di-Cup 40C Peroxide

**Category :** Polymer , Thermoset , Polyester, TS , Polyurethane, TS , Thermoset Polyurethane, Elastomer, Unreinforced , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

Millathane® 76 is a very suitable choice for use in products such as bushings, small copier rolls; automotive applications – bumpers, o-rings, hydraulic seals, belts, gaskets, solid tires – and many other high performance polyurethane applications. Millathane 76 can be vulcanized by sulfur or peroxide cured systems. Curing of Millathane®76 can easily be done with many types of peroxides. Millathane76 peroxide vulcanizates have superior compression set, greater heat stability, and are more resistant to reversion than sulfur cures. Formulation Millathane 76 100.0 Stearic Acid 0.5 N-220 Black 20.0 Di-Cup 40C 4.0 All information provided by TSE Industries

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_TSE-Industries-Millathane-76-Millable-Polyester-Polyurethane-Rubber-40-PHR-Di-Cup-40C-Peroxide.php](http://www.lookpolymers.com/polymer_TSE-Industries-Millathane-76-Millable-Polyester-Polyurethane-Rubber-40-PHR-Di-Cup-40C-Peroxide.php)

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	68	68	
Tensile Strength, Yield	30.23 MPa	4384 psi	
Elongation at Yield	277 %	277 %	
100% Modulus	0.00466 GPa	0.676 ksi	
200% Modulus	0.01726 GPa	2.504 ksi	
Tear Strength	59.7 kN/m	341 pli	Die C
Compression Set	17 % @Temperature 100 °C, Time 79200 sec	17 % @Temperature 212 °F, Time 22.0 hour	

Processing Properties	Metric	English	Comments
Cure Time	15.0 min @Temperature 160 °C	0.250 hour @Temperature 320 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China