

## TSE Industries Millathane® 76 Millable Polyester Polyurethane Rubber, Hardness 50A, Black Peroxide Cure

Category : Polymer , Thermoset , Polyester, TS , Polyurethane, TS , Thermoset Polyurethane, Elastomer, Unreinforced , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

Millathane® 76 is a very suitable choice for use in products such as bushings, small copier rolls; automotive applications – bumpers, o-rings, hydraulic seals, belts, gaskets, solid tires – and many other high performance polyurethane applications. Millathane 76 can be vulcanized by sulfur or peroxide cured systems. Formulation Millathane 76 100.0Stearic Acid0.5N-550 Black30.0TP-9520.0Akrofax 7585.0Di-Cup 40C2.0All information provided by TSE Industries

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_TSE-Industries-Millathane-76-Millable-Polyester-Polyurethane-Rubber-Hardness-50A-Black-Peroxide-Cure.php](http://www.lookpolymers.com/polymer_TSE-Industries-Millathane-76-Millable-Polyester-Polyurethane-Rubber-Hardness-50A-Black-Peroxide-Cure.php)

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	50	50	
Tensile Strength, Yield	17.31 MPa	2511 psi	
Elongation at Yield	491 %	491 %	
100% Modulus	0.00150 GPa	0.218 ksi	
200% Modulus	0.00412 GPa	0.598 ksi	
300% Modulus	0.007812 GPa	1.133 ksi	
Tear Strength	42.2 kN/m	241 pli	Die C

Processing Properties	Metric	English	Comments
Cure Time	15.0 min	0.250 hour	
	@Temperature 160 °C	@Temperature 320 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China