

## TSE Industries Millathane® 97 Millable Polyester Polyurethane Rubber, 30.0 PHR Wacker HDK N20 Filler

Category : Polymer , Thermoset , Polyester, TS , Polyurethane, TS , Thermoset Polyurethane, Elastomer, Unreinforced , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

Millathane 97 is a polyether polyurethane rubber having excellent transparency, good wear properties, a high coefficient of friction and very good UV stability. This polyurethane rubber is designed for applications in shoe soling, roll coverings and all other applications where transparent, brightly colored or decorative products are desired. Formulation Millathane 97 100.0 Stearic Acid 0.3 Wacker HDK N20 (fumed silica) 30.0 Luperox 2310.4 SR-231 (DEGDMA) 3.0 Irganox 10100.2 All information provided by TSE Industries

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_TSE-Industries-Millathane-97-Millable-Polyester-Polyurethane-Rubber-300-PHR-Wacker-HDK-N20-Filler.php](http://www.lookpolymers.com/polymer_TSE-Industries-Millathane-97-Millable-Polyester-Polyurethane-Rubber-300-PHR-Wacker-HDK-N20-Filler.php)

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	66	66	
Tensile Strength, Yield	25.2 MPa	3650 psi	
Elongation at Yield	633 %	633 %	
100% Modulus	0.00162 GPa	0.235 ksi	
200% Modulus	0.00214 GPa	0.310 ksi	
300% Modulus	0.00331 GPa	0.480 ksi	
Tear Strength	32.9 kN/m	188 pli	Die C

Optical Properties	Metric	English	Comments
Transmission, Visible	90 %	90 %	transparent; thickness not quantified

Processing Properties	Metric	English	Comments
Cure Time	8.00 min	0.133 hour	
	@Temperature 149 °C	@Temperature 300 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China