

## TSE Industries Millathane® CM Millable Polyether Urethane Rubber, 0.0 PHR Caytur 4

Category: Polymer, Thermoset, Polyester, TS, Polyurethane, TS, Thermoset Polyurethane, Elastomer, Unreinforced, Rubber or Thermoset Elastomer (TSE)

## **Material Notes:**

MILLATHANE CM is a sulfur and peroxide curable polyether urethane rubber. Its outstanding property is its great resistance to abrasion, which makes it of special interest for articles that are subjected to high wear in service. It has a unique combination of excellent properties, such as low temperature characteristics, and resistance to heat deterioration, ozone cracking, weathering and swelling in oils or solvents. An activator containing zinc should be used to insure faster rates of cure in reasonable periods of time. Zinc diethyldithiocarbamate and zinc dibutyldithiocarbamate over the range of 0.1 to 1.0 phr have been used, but they do not give cures as satisfactory as the ZnCl2/MBTS complex known as CAYTUR 4. Formulation Millathane CM 100.0N330 Carbon Black30.0 Coumarone-Indene Resin15.0 MBTS4.0 MBTS4.0 MBTS1.0 Sulfur0.75 CAYTUR 40.0 Zinc Stearate0.5 All information provided by TSE Industries

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_TSE-Industries-Millathane-CM-Millable-Polyether-Urethane-Rubber-00-PHR-Caytur-4.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	68	68	
Tensile Strength, Yield	25.5 MPa	3700 psi	
Elongation at Break	550 %	550 %	
300% Modulus	0.00621 GPa	0.900 ksi	
Tear Strength	64.7 kN/m	369 pli	Die C; ASTM D624
Abrasion	365	365	NBS Index
Compression Set	24 %	24 %	Method B
	@Temperature 70.0 °C, Time 79200 sec	@Temperature 158 °F, Time 22.0 hour	

Processing Properties	Metric	English	Comments
Cure Time	60.0 min	1.00 hour	
	@Temperature 142 °C	@Temperature 287 °F	

Descriptive Properties	Value	Comments
Mooney Scorch	>30	time to 10 point rise (minutes) at 250°F
	30	time to 10 point rise (minutes) at 275°F

## Contact Songhan Plastic Technology Co.,Ltd.



Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China