

## TSE Industries Millathane® CM Millable Polyether Urethane Rubber, 0.75 PHR Sulfur

Category : Polymer , Thermoset , Polyester, TS , Polyurethane, TS , Thermoset Polyurethane, Elastomer, Unreinforced , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

MILLATHANE CM is a sulfur and peroxide curable polyether urethane rubber. Its outstanding property is its great resistance to abrasion, which makes it of special interest for articles that are subjected to high wear in service. It has a unique combination of excellent properties, such as low temperature characteristics, and resistance to heat deterioration, ozone cracking, weathering and swelling in oils or solvents. Increasing the concentration of sulfur produces a faster rate and a higher state of cure – better abrasion resistance, better dynamic properties, and high hardness – equivalent compression set, and somewhat poorer aging properties. Decreasing the sulfur content results in a reduced state of cure. Formulation Millathane CM 100.0N330 Carbon Black30.0Coumarone-Indene Resin15.0MBTS4.0MBT1.0Zinc Stearate0.75CAYTUR 40.35Sulfur0.75All information provided by TSE Industries

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_TSE-Industries-Millathane-CM-Millable-Polyether-Urethane-Rubber-075-PHR-Sulfur.php](http://www.lookpolymers.com/polymer_TSE-Industries-Millathane-CM-Millable-Polyether-Urethane-Rubber-075-PHR-Sulfur.php)

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	65	65	
	68	68	after 7 days at 100°C
Tensile Strength, Yield	27.9 MPa	4050 psi	after 7 days at 100°C
	31.0 MPa	4500 psi	
Elongation at Break	390 %	390 %	after 7 days at 100°C
	480 %	480 %	
300% Modulus	0.01465 GPa	2.125 ksi	
	0.01948 GPa	2.825 ksi	after 7 days at 100°C
Abrasion	335	335	NBS Index
Compression Set	19 %	19 %	Method B
	@Temperature 70.0 °C, Time 79200 sec	@Temperature 158 °F, Time 22.0 hour	

Processing Properties	Metric	English	Comments
Cure Time	60.0 min	1.00 hour	
	@Temperature 142 °C	@Temperature 287 °F	

Descriptive Properties	Value	Comments
?T, Platen (°C)	60	

Descriptive Properties	Value	Comments
Heat build-up, Internal Temp (°C)	25	Goodrich Flexometer

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China