

## TSE Industries Millathane® CM Millable Polyether Urethane Rubber, Hardness 75A

Category : Polymer , Thermoset , Polyester, TS , Polyurethane, TS , Thermoset Polyurethane, Elastomer, Unreinforced , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

MILLATHANE CM is a sulfur and peroxide curable polyether urethane rubber. Its outstanding property is its great resistance to abrasion, which makes it of special interest for articles that are subjected to high wear in service. It has a unique combination of excellent properties, such as low temperature characteristics, and resistance to heat deterioration, ozone cracking, weathering and swelling in oils or solvents. Formulation Millathane CM 100.0Hi-Sil 23345.0Cumar W 2 1/215.0MBTS4.0MBT2.0Sulfur1.5CAYTUR 41.0Zinc Stearate0.5All information provided by TSE Industries

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_TSE-Industries-Millathane-CM-Millable-Polyether-Urethane-Rubber-Hardness-75A.php](http://www.lookpolymers.com/polymer_TSE-Industries-Millathane-CM-Millable-Polyether-Urethane-Rubber-Hardness-75A.php)

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	75	75	
Tensile Strength, Yield	35.9 MPa	5200 psi	
Elongation at Yield	600 %	600 %	
100% Modulus	0.00224 GPa	0.325 ksi	
300% Modulus	0.00689 GPa	1.00 ksi	
Tear Strength	52.6 kN/m	300 pli	Graves
Compression Set	70 % @Temperature 70.0 °C, Time 79200 sec	70 % @Temperature 158 °F, Time 22.0 hour	Method B

Processing Properties	Metric	English	Comments
Cure Time	15.0 min @Temperature 154 °C	0.250 hour @Temperature 310 °F	

Descriptive Properties	Value	Comments
500% Modulus (ksi)	2.85	
Mooney Scorch	>= 55	at 250°F; 22 minutes to a 10 point rise

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China