

## TSE Industries Millathane® CM Millable Polyether Urethane Rubber with 30 PHR N330 Filler

Category: Polymer, Thermoset, Polyester, TS, Polyurethane, TS, Thermoset Polyurethane, Elastomer, Unreinforced, Rubber or Thermoset Elastomer (TSE)

## **Material Notes:**

MILLATHANE CM is a sulfur and peroxide curable polyether urethane rubber. Its outstanding property is its great resistance to abrasion, which makes it of special interest for articles that are subjected to high wear in service. It has a unique combination of excellent properties, such as low temperature characteristics, and resistance to heat deterioration, ozone cracking, weathering and swelling in oils or solvents. Formulation Millathane CM 100.0N33030.0 Coumarone-Indene Resin10.0 MBTS 4.0 MBT1.0 Sulfur 0.75 CAYTUR 40.35 Zinc Stearate 0.50 All information provided by TSE Industries

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_TSE-Industries-Millathane-CM-Millable-Polyether-Urethane-Rubber-with-30-PHR-N330-Filler.php

| Physical Properties | Metric              | English             | Comments |
|---------------------|---------------------|---------------------|----------|
| Specific Gravity    | 1.18 g/cc           | 1.18 g/cc           |          |
| Mooney Viscosity    | 30                  | 30                  |          |
|                     | @Temperature 121 °C | @Temperature 250 °F |          |

| Mechanical Properties   | Metric      | English   | Comments  |
|-------------------------|-------------|-----------|-----------|
| Hardness, Shore A       | 66          | 66        |           |
| Tensile Strength, Yield | 37.9 MPa    | 5500 psi  |           |
| Elongation at Yield     | 540 %       | 540 %     |           |
| 100% Modulus            | 0.00293 GPa | 0.425 ksi |           |
| 300% Modulus            | 0.0128 GPa  | 1.85 ksi  |           |
| Tear Strength           | 56.7 kN/m   | 324 pli   | Graves    |
| Abrasion                | 335         | 335       | NBS Index |
| Compression Set         | 22 %        | 22 %      | Method B  |

| Processing Properties | Metric              | English             | Comments |
|-----------------------|---------------------|---------------------|----------|
| Cure Time             | 60.0 min            | 1.00 hour           |          |
|                       | @Temperature 142 °C | @Temperature 287 °F |          |

## Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com



Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China