

TSE Industries Millathane® E34 Millable Polyether Polyurethane Rubber with 1.0 PHR Zinc Stearate

Category : Polymer , Thermoset , Polyester, TS , Polyurethane, TS , Thermoset Polyurethane, Elastomer, Unreinforced , Rubber or Thermoset Elastomer (TSE)

Material Notes:

MILLATHANE E34 is a high performance polyether polyurethane rubber for applications requiring: high abrasion resistance, low temperature flexibility, ozone resistance, oil and fuel resistance, outstanding hydrolytic stability and improved processing. MILLATHANE E34 can be compounded and processed by the use of conventional rubber manufacturing equipment – mixed on two roll mills or an internal mixer. Compounds can be – calendered; extruded; injection, transfer, or compression molded – to produce finished polyurethane parts. It can be vulcanized by organic peroxides or sulfur with thiazole accelerators. Formulation Millathane E34 100.0N330 Black30.0Cumar P1010.0MBTS4.0MBT2.0Sulfur1.5Thanecure® ZM1.0Zinc Stearate1.0All information provided by TSE Industries

Order this product through the following link:

http://www.lookpolymers.com/polymer_TSE-Industries-Millathane-E34-Millable-Polyether-Polyurethane-Rubber-with-10-PHR-Zinc-Stearate.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	>= 65	>= 65	
Tensile Strength, Yield	29.30 MPa	4249 psi	
Elongation at Yield	565 %	565 %	
100% Modulus	0.00270 GPa	0.392 ksi	
200% Modulus	0.00580 GPa	0.841 ksi	
300% Modulus	0.009701 GPa	1.407 ksi	
Tear Strength	34.6 kN/m	197 pli	Die C
Compression Set	31.7 % @Temperature 70.0 °C, Time 79200 sec	31.7 % @Temperature 158 °F, Time 22.0 hour	

Processing Properties	Metric	English	Comments
Cure Time	9.50 min @Temperature 68.3 °C	0.158 hour @Temperature 155 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China