

## TSE Industries Millathane® E34 Millable Polyether Polyurethane Rubber with 2.0 PHR Di-Cup 40C

Category : Polymer , Thermoset , Polyester, TS , Polyurethane, TS , Thermoset Polyurethane, Elastomer, Unreinforced , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

MILLATHANE E34 is a high performance polyether polyurethane rubber for applications requiring: high abrasion resistance, low temperature flexibility, ozone resistance, oil and fuel resistance, outstanding hydrolytic stability and improved processing. MILLATHANE E34 can be compounded and processed by the use of conventional rubber manufacturing equipment – mixed on two roll mills or an internal mixer. Compounds can be – calendered; extruded; injection, transfer, or compression molded – to produce finished polyurethane parts. It can be vulcanized by organic peroxides or sulfur with thiazole accelerators. Formulation Millathane E34 100.0 Stearic Acid 0.5 N220 Black 20.0 Di-Cup 40C 2.0 All information provided by TSE Industries

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_TSE-Industries-Millathane-E34-Millable-Polyether-Polyurethane-Rubber-with-20-PHR-Di-Cup-40C.php](http://www.lookpolymers.com/polymer_TSE-Industries-Millathane-E34-Millable-Polyether-Polyurethane-Rubber-with-20-PHR-Di-Cup-40C.php)

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	>= 55	>= 55	
Tensile Strength, Yield	20.10 MPa	2915 psi	
Elongation at Yield	583 %	583 %	
100% Modulus	0.00130 GPa	0.189 ksi	
200% Modulus	0.00240 GPa	0.348 ksi	
300% Modulus	0.00480 GPa	0.696 ksi	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China