

TSE Industries Millathane® E34 Millable Polyether Polyurethane Rubber with 2.0 PHR MBTS

Category : Polymer , Thermoset , Polyester, TS , Polyurethane, TS , Thermoset Polyurethane, Elastomer, Unreinforced , Rubber or Thermoset Elastomer (TSE)

Material Notes:

MILLATHANE E34 is a high performance polyether polyurethane rubber for applications requiring: high abrasion resistance, low temperature flexibility, ozone resistance, oil and fuel resistance, outstanding hydrolytic stability and improved processing. MILLATHANE E34 can be compounded and processed by the use of conventional rubber manufacturing equipment – mixed on two roll mills or an internal mixer. Compounds can be – calendered; extruded; injection, transfer, or compression molded – to produce finished polyurethane parts. It can be vulcanized by organic peroxides or sulfur with thiazole accelerators. Formulation Millathane E34 100 Zinc Stearate 0.5N330 Black 30.0 Cumar P1010.0 MBT 2.0 Thanecure® ZM1.0 Sulfur 1.5 MBTS 2.0 All information provided by TSE Industries

Order this product through the following link:

http://www.lookpolymers.com/polymer_TSE-Industries-Millathane-E34-Millable-Polyether-Polyurethane-Rubber-with-20-PHR-MBTS.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	>= 60	>= 60	
Tensile Strength, Yield	30.0 MPa	4350 psi	
Elongation at Yield	624 %	624 %	
100% Modulus	0.00220 GPa	0.319 ksi	
200% Modulus	0.00450 GPa	0.653 ksi	
300% Modulus	0.00800 GPa	1.16 ksi	
Tear Strength	32.5 kN/m	185 pli	Die C
Compression Set	39.4 % @Temperature 70.0 °C, Time 79200 sec	39.4 % @Temperature 158 °F, Time 22.0 hour	

Processing Properties	Metric	English	Comments
Cure Time	7.50 min @Temperature 155 °C	0.125 hour @Temperature 311 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China