

## TSE Industries Millathane® E34 Millable Polyether Polyurethane Rubber with 40 PHR Hi-Sil 233 Filler

Category : Polymer , Thermoset , Polyester, TS , Polyurethane, TS , Thermoset Polyurethane, Elastomer, Unreinforced , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

MILLATHANE E34 is a high performance polyether polyurethane rubber for applications requiring: high abrasion resistance, low temperature flexibility, ozone resistance, oil and fuel resistance, outstanding hydrolytic stability and improved processing. MILLATHANE E34 can be compounded and processed by the use of conventional rubber manufacturing equipment – mixed on two roll mills or an internal mixer. Compounds can be – calendered; extruded; injection, transfer, or compression molded – to produce finished polyurethane parts. It can be vulcanized by organic peroxides or sulfur with thiazole accelerators. Formulation Millathane E34 100.0 Zinc Stearate 0.5 MBT 4.0 MBT 2.0 Thanecure® ZM1.0 Sulfur 1.5 Cumar P10 10.0 Precipitated Silica - Hi-Sil 233 40 All information provided by TSE Industries

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_TSE-Industries-Millathane-E34-Millable-Polyether-Polyurethane-Rubber-with-40-PHR-Hi-Sil-233-Filler.php](http://www.lookpolymers.com/polymer_TSE-Industries-Millathane-E34-Millable-Polyether-Polyurethane-Rubber-with-40-PHR-Hi-Sil-233-Filler.php)

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	>= 68	>= 68	
Tensile Strength, Yield	28.59 MPa	4147 psi	
Elongation at Yield	737 %	737 %	
100% Modulus	0.00180 GPa	0.261 ksi	
200% Modulus	0.00300 GPa	0.435 ksi	
300% Modulus	0.00490 GPa	0.711 ksi	
Tear Strength	34.9 kN/m	199 pli	Die C

Processing Properties	Metric	English	Comments
Cure Time	17.0 min @Temperature 68.3 °C	0.283 hour @Temperature 155 °F	Press cured

Descriptive Properties	Value	Comments
DIN Abrasion (mm <sup>3</sup> )	51.8	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**