

TSE Industries Millathane® E34 Millable Polyether Polyurethane Rubber with Sundex 790

Category : Polymer , Thermoset , Polyester, TS , Polyurethane, TS , Thermoset Polyurethane, Elastomer, Unreinforced , Rubber or Thermoset Elastomer (TSE)

Material Notes:

MILLATHANE E34 is a high performance polyether polyurethane rubber for applications requiring: high abrasion resistance, low temperature flexibility, ozone resistance, oil and fuel resistance, outstanding hydrolytic stability and improved processing. MILLATHANE E34 can be compounded and processed by the use of conventional rubber manufacturing equipment – mixed on two roll mills or an internal mixer. Compounds can be – calendered; extruded; injection, transfer, or compression molded – to produce finished polyurethane parts. It can be vulcanized by organic peroxides or sulfur with thiazole accelerators. Formulation Millathane E34 100.0 Zinc Stearate 0.5N-330 Black 30.0 MBTS 4.0 MBT 2.0 Thanecure® ZM1.0 Sulfur 1.5 Sundex 790 10.0 All information provided by TSE Industries

Order this product through the following link:

http://www.lookpolymers.com/polymer_TSE-Industries-Millathane-E34-Millable-Polyether-Polyurethane-Rubber-with-Sundex-790.php

| Mechanical Properties | Metric | English | Comments |
|-----------------------|--------|---------|----------|
| Hardness, Shore A | >= 66 | >= 66 | |

| Thermal Properties | Metric | English | Comments |
|----------------------------------|----------|----------|--|
| Minimum Service Temperature, Air | -48.0 °C | -54.4 °F | Retraction Temperature, TR10; ASTM D1329 |
| Brittleness Temperature | -90.0 °C | -130 °F | ASTM D746 |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China