

## TSE Industries Millathane® HT High Temperature-Resistant Millable Polyester Polyurethane, 300°F Cure Temperature

Category : Polymer , Thermoset , Polyester, TS , Polyurethane, TS , Thermoset Polyurethane, Elastomer, Unreinforced , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

MILLATHANE HT is a polyester millable polyurethane which has the ability to withstand elevated temperatures. Polyurethanes have been known for their excellent resistance to abrasion, impact, tear strength, oil and fuel resistance, and ozone resistance. The life expectancy of urethane is often 5 times longer than other elastomers, thus saving material costs and downtime expense. One shortcoming of polyurethanes is loss of physical properties at temperatures over 180°F (82°C). MILLATHANE HT has overcome this weakness. Formulation Millathane HT 100.0 Zinc Stearate 0.5 MBTS 4.0 MBT 2.0 N-330 Black 20.0 Sulfur 1.5 THANECURE® ZM1.0 All information provided by TSE Industries

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_TSE-Industries-Millathane-HT-High-Temperature-Resistant-Millable-Polyester-Polyurethane-300F-Cure-Temperature.php](http://www.lookpolymers.com/polymer_TSE-Industries-Millathane-HT-High-Temperature-Resistant-Millable-Polyester-Polyurethane-300F-Cure-Temperature.php)

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	62	62	
Tensile Strength, Yield	27.16 MPa	3939 psi	
Elongation at Yield	403 %	403 %	
100% Modulus	0.00312 GPa	0.452 ksi	
200% Modulus	0.008467 GPa	1.228 ksi	
300% Modulus	0.01576 GPa	2.286 ksi	
Tear Strength	51.8 kN/m	296 pli	Die C

Processing Properties	Metric	English	Comments
Cure Time	25.0 min	0.417 hour	
	@Temperature 149 °C	@Temperature 300 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China