

TSE Industries Millathane® HT High Temperature-Resistant Millable Polyester Polyurethane with 0.0 PHR MBTS

Category: Polymer, Thermoset, Polyester, TS, Polyurethane, TS, Thermoset Polyurethane, Elastomer, Unreinforced, Rubber or Thermoset Elastomer (TSE)

Material Notes:

MILLATHANE HT is a polyester millable polyurethane which has the ability to withstand elevated temperatures. Polyurethanes have been known for their excellent resistance to abrasion, impact, tear strength, oil and fuel resistance, and ozone resistance. The life expectancy of urethane is often 5 times longer than other elastomers, thus saving material costs and downtime expense. One shortcoming of polyurethanes is loss of physical properties at temperatures over 180°F (82°C). MILLATHANE HT has overcome this weakness. An increase in the level of MBTS results in more processing safety, plus it gives a higher state of cure. On the other hand, MBT acts as an accelerator which, when increased, will cause a decrease in processing safety and a higher state of cure. All information provided by TSE Industries

Order this product through the following link:

http://www.lookpolymers.com/polymer_TSE-Industries-Millathane-HT-High-Temperature-Resistant-Millable-Polyester-Polyurethane-with-00-PHR-MBTS.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	79	79	
Tensile Strength, Yield	15.89 MPa	2304 psi	
Elongation at Yield	717 %	717 %	
100% Modulus	0.00283 GPa	0.410 ksi	
200% Modulus	0.00541 GPa	0.784 ksi	
300% Modulus	0.008170 GPa	1.185 ksi	
Tear Strength	64.0 kN/m	365 pli	Die C
Compression Set	79 %	79 %	
	@Temperature 70.0 °C, Time 79200 sec	@Temperature 158 °F, Time 22.0 hour	

Processing Properties	Metric	English	Comments
Cure Time	6.00 min	0.100 hour	Press cured
	@Temperature 160 °C	@Temperature 320 °F	

Descriptive Properties	Value	Comments
DIN Abrasion (mm³)	140	

Contact Songhan Plastic Technology Co.,Ltd.



Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China