

## TSE Industries Millathane® HT High Temperature-Resistant Millable Polyester Polyurethane with 20 PHR Laminar Filler

Category : Polymer , Thermoset , Polyester, TS , Polyurethane, TS , Thermoset Polyurethane, Elastomer, Unreinforced , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

MILLATHANE HT is a polyester millable polyurethane which has the ability to withstand elevated temperatures. Polyurethanes have been known for their excellent resistance to abrasion, impact, tear strength, oil and fuel resistance, and ozone resistance. The life expectancy of urethane is often 5 times longer than other elastomers, thus saving material costs and downtime expense. One shortcoming of polyurethanes is loss of physical properties at temperatures over 180°F (82°C). MILLATHANE HT has overcome this weakness. Formulation Millathane HT 100.0 Zinc Stearate 0.5 MBTS 4.0 MBT 2.0 THANECURE® ZM1.0 Sulfur 1.5 Laminar 20 All information provided by TSE Industries

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_TSE-Industries-Millathane-HT-High-Temperature-Resistant-Millable-Polyester-Polyurethane-with-20-PHR-Laminar-Filler.php](http://www.lookpolymers.com/polymer_TSE-Industries-Millathane-HT-High-Temperature-Resistant-Millable-Polyester-Polyurethane-with-20-PHR-Laminar-Filler.php)

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	54	54	
Tensile Strength, Yield	10.6 MPa	1540 psi	
Elongation at Yield	426 %	426 %	
100% Modulus	0.00179 GPa	0.260 ksi	
200% Modulus	0.00294 GPa	0.427 ksi	
300% Modulus	0.00456 GPa	0.662 ksi	
Tear Strength	26.4 kN/m	151 pli	Die C
Compression Set	57 % @Temperature 70.0 °C, Time 79200 sec	57 % @Temperature 158 °F, Time 22.0 hour	

Processing Properties	Metric	English	Comments
Cure Time	20.0 min @Temperature 154 °C	0.333 hour @Temperature 310 °F	Press cured

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China