

## TSE Industries Millathane® HT High Temperature-Resistant Millable Polyester Polyurethane with 30 PHR N774 (SRF) Filler

Category : Polymer , Thermoset , Polyester, TS , Polyurethane, TS , Thermoset Polyurethane, Elastomer, Unreinforced , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

MILLATHANE HT is a polyester millable polyurethane which has the ability to withstand elevated temperatures. Polyurethanes have been known for their excellent resistance to abrasion, impact, tear strength, oil and fuel resistance, and ozone resistance. The life expectancy of urethane is often 5 times longer than other elastomers, thus saving material costs and downtime expense. One shortcoming of polyurethanes is loss of physical properties at temperatures over 180°F (82°C). MILLATHANE HT has overcome this weakness. Formulation Millathane HT100.0Zinc Stearate0.5MBTS4.0MBT2.0THANECURE® ZM1.0Sulfur1.5N774 (SRF)30All information provided by TSE Industries

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_TSE-Industries-Millathane-HT-High-Temperature-Resistant-Millable-Polyester-Polyurethane-with-30-PHR-N774-SRF-Filler.php](http://www.lookpolymers.com/polymer_TSE-Industries-Millathane-HT-High-Temperature-Resistant-Millable-Polyester-Polyurethane-with-30-PHR-N774-SRF-Filler.php)

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	64	64	
Tensile Strength, Yield	20.02 MPa	2903 psi	
Elongation at Yield	398 %	398 %	
100% Modulus	0.00382 GPa	0.554 ksi	
200% Modulus	0.009611 GPa	1.394 ksi	
300% Modulus	0.01509 GPa	2.188 ksi	
Tear Strength	47.4 kN/m	270 pli	Die C
Taber Abrasion, mg/1000 Cycles	0.090	0.090	H-18, mg loss/rev
Compression Set	63 % @Temperature 70.0 °C, Time 79200 sec	63 % @Temperature 158 °F, Time 22.0 hour	

Processing Properties	Metric	English	Comments
Cure Time	20.0 min @Temperature 149 °C	0.333 hour @Temperature 300 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**