

## TSE Industries Millathane® HT High Temperature-Resistant Millable Polyester Polyurethane with 4.0 PHR MBTS

**Category :** Polymer , Thermoset , Polyester, TS , Polyurethane, TS , Thermoset Polyurethane, Elastomer, Unreinforced , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

MILLATHANE HT is a polyester millable polyurethane which has the ability to withstand elevated temperatures. Polyurethanes have been known for their excellent resistance to abrasion, impact, tear strength, oil and fuel resistance, and ozone resistance. The life expectancy of urethane is often 5 times longer than other elastomers, thus saving material costs and downtime expense. One shortcoming of polyurethanes is loss of physical properties at temperatures over 180°F (82°C). MILLATHANE HT has overcome this weakness. An increase in the level of MBTS results in more processing safety, plus it gives a higher state of cure. On the other hand, MBT acts as an accelerator which, when increased, will cause a decrease in processing safety and a higher state of cure. All information provided by TSE Industries

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_TSE-Industries-Millathane-HT-High-Temperature-Resistant-Millable-Polyester-Polyurethane-with-40-PHR-MBTS.php](http://www.lookpolymers.com/polymer_TSE-Industries-Millathane-HT-High-Temperature-Resistant-Millable-Polyester-Polyurethane-with-40-PHR-MBTS.php)

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	80	80	
Tensile Strength, Yield	18.30 MPa	2654 psi	
Elongation at Yield	414 %	414 %	
100% Modulus	0.00567 GPa	0.823 ksi	
200% Modulus	0.01159 GPa	1.681 ksi	
300% Modulus	0.01595 GPa	2.313 ksi	
Tear Strength	40.0 kN/m	228 pli	Die C
Compression Set	58 % @Temperature 70.0 °C, Time 79200 sec	58 % @Temperature 158 °F, Time 22.0 hour	

Processing Properties	Metric	English	Comments
Cure Time	12.0 min @Temperature 160 °C	0.200 hour @Temperature 320 °F	Press cured

Descriptive Properties	Value	Comments
DIN Abrasion (mm³)	115	

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China