

## Taiwan PU Corporation CPU-69-A/B Mixing Ratio 100/28 Polyurethane Casting Elastomer

Category : Polymer , Thermoset , Polyurethane, TS , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

Compound of CPU-69-A/B with a mixing ratio of 100/28. Information provided by Taiwan PU Corporation. MatWeb has a separate entry for the unmixed A and B components.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Taiwan-PU-Corporation-CPU-69-AB-Mixing-Ratio-10028-Polyurethane-Casting-Elastomer.php](http://www.lookpolymers.com/polymer_Taiwan-PU-Corporation-CPU-69-AB-Mixing-Ratio-10028-Polyurethane-Casting-Elastomer.php)

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	60	60	
Tensile Strength at Break	4.51 MPa	654 psi	
Elongation at Break	550 %	550 %	
Tear Strength	24.5 kN/m	140 pli	

Descriptive Properties	Value	Comments
Mixing Ratio	100/28	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China