

Taiwan PU Corporation CPU-69-A/B Mixing Ratio 100/36 Polyurethane Casting Elastomer

Category : Polymer , Thermoset , Polyurethane, TS , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Compound of CPU-69-A/B with a mixing ratio of 100/36. Information provided by Taiwan PU Corporation. MatWeb has a separate entry for the unmixed A and B components.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Taiwan-PU-Corporation-CPU-69-AB-Mixing-Ratio-10036-Polyurethane-Casting-Elastomer.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	83	83	
Tensile Strength at Break	14.51 MPa	2105 psi	
Elongation at Break	250 %	250 %	
Tear Strength	30.4 kN/m	174 pli	

Descriptive Properties	Value	Comments
Mixing Ratio	100/36	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China