

Taiwan PU Corporation PPG CPU-2079 Polyurethane Casting Elastomer

Category : Polymer , Thermoset , Polyurethane, TS , Rubber or Thermoset Elastomer (TSE)

Material Notes:

A urethane elastomer that can be cured by reacting with a polyamine or a polyolhardener. The molding process is composed of pre-heating, degassing, maxing with a hardener, pouring into the mold, curing, demolding and after curing. Information provided by Taiwan PU Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Taiwan-PU-Corporation-PPG-CPU-2079-Polyurethane-Casting-Elastomer.php

Physical Properties	Metric	English	Comments
Viscosity	9000 - 14000 cP	9000 - 14000 cP	
	@Temperature 40.0 Â°C	@Temperature 104 Â°F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	78 - 82	78 - 82	
Tensile Strength at Break	17.16 - 26.97 MPa	2489 - 3912 psi	
Elongation at Break	510 - 660 %	510 - 660 %	
Tear Strength	73.5 - 113 kN/m	420 - 644 pli	

Processing Properties	Metric	English	Comments
Processing Temperature	100 Â°C	212 Â°F	Working Temperature, Prepolymer
Mold Temperature	100 Â°C	212 Â°F	
Pot Life	11 min	11 min	

Descriptive Properties	Value	Comments
MOCA Temperature	110Â°C	
NCO Content	Max 4%	
	Min 3.6%	
PHR of MOCA	11%	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China