

## Taiwan PU Corporation TPU-CH75 High Hydrolysis Resistance, Calender Molding Polyether Base TPU

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyurethane, TP , Thermoplastic Polyurethane (TPUR), Polyether Grade

### Material Notes:

Thermoplastic Polyurethane (TPU), High Hydrolysis Resistance, Polyether Base, Calender Molding Information provided by Taiwan PU Corporation.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Taiwan-PU-Corporation-TPU-CH75-High-Hydrolysis-Resistance-Calender-Molding-Polyether-Base-TPU.php](http://www.lookpolymers.com/polymer_Taiwan-PU-Corporation-TPU-CH75-High-Hydrolysis-Resistance-Calender-Molding-Polyether-Base-TPU.php)

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	25	25	
Tensile Strength at Break	20.59 MPa	2986 psi	
Elongation at Break	900 %	900 %	
100% Modulus	0.00340 GPa	0.493 ksi	
300% Modulus	0.00340 GPa	0.493 ksi	
Resilience	65	65	%, Impact Resilience
Taber Abrasion, mg/1000 Cycles	30	30	

Processing Properties	Metric	English	Comments
Feed Temperature	165 Â°C	329 Â°F	
Middle Barrel Temperature	170 Â°C	338 Â°F	Compress zone
Front Barrel Temperature	175 Â°C	347 Â°F	Metering zone
Adapter Temperature	180 Â°C	356 Â°F	
Die Temperature	180 Â°C	356 Â°F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China