

Taiwan PU Corporation TPUI-E85 General Grade, Injection Molding Polyester Base TPU

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyurethane, TP , Thermoplastic Polyurethane (TPUR), Polyester Grade

Material Notes:

Thermoplastic Polyurethane (TPU), General Grade, Polyester Base, Injection Molding Information provided by Taiwan PU Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Taiwan-PU-Corporation-TPUI-E85-General-Grade-Injection-Molding-Polyester-Base-TPU.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	85	85	
Tensile Strength at Break	35.3 MPa	5120 psi	
Elongation at Break	700 %	700 %	
100% Modulus	0.00690 GPa	1.00 ksi	
300% Modulus	0.0108 GPa	1.57 ksi	
Resilience	40	40	%, Impact Resilience
Taber Abrasion, mg/1000 Cycles	35	35	

Processing Properties	Metric	English	Comments
Feed Temperature	180 Â°C	356 Â°F	
Middle Barrel Temperature	185 Â°C	365 Â°F	Compress zone
Front Barrel Temperature	190 Â°C	374 Â°F	Metering zone
Adapter Temperature	195 Â°C	383 Â°F	
Die Temperature	195 Â°C	383 Â°F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China