

Taiwan PU Corporation TPUI-ED64 General Grade, Injection Molding Polyester Base TPU

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyurethane, TP , Thermoplastic Polyurethane (TPUR), Polyester Grade

Material Notes:

Thermoplastic Polyurethane (TPU), General Grade, Polyester Base, Injection Molding Information provided by Taiwan PU Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Taiwan-PU-Corporation-TPUI-ED64-General-Grade-Injection-Molding-Polyester-Base-TPU.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	64	64	
Tensile Strength at Break	47.07 MPa	6827 psi	
Elongation at Break	450 %	450 %	
100% Modulus	0.0206 GPa	2.99 ksi	
300% Modulus	0.0304 GPa	4.41 ksi	
Resilience	25	25	%, Impact Resilience
Taber Abrasion, mg/1000 Cycles	20	20	

Processing Properties	Metric	English	Comments
Feed Temperature	195 Â°C	383 Â°F	
Middle Barrel Temperature	200 Â°C	392 Â°F	Compress zone
Front Barrel Temperature	210 Â°C	410 Â°F	Metering zone
Adapter Temperature	215 Â°C	419 Â°F	
Die Temperature	215 Â°C	419 Â°F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China