

Taiwan Sheen Soon Sheenthane® A9610 Thermoplastic Polyurethane Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyurethane TPE , Polyurethane, TP

Material Notes:

Thermoplastic polyurethane elastomer for injection molding Information provided by Taiwan Sheen Soon Co., LTD.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Taiwan-Sheen-Soon-Sheenthane-A9610-Thermoplastic-Polyurethane-Elastomer.php

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in ³	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	94 - 98	94 - 98	
Tensile Strength	49.0 MPa	7110 psi	
Elongation at Break	500 %	500 %	
100% Modulus	0.01175 GPa	1.704 ksi	
300% Modulus	0.0226 GPa	3.27 ksi	

Processing Properties	Metric	English	Comments
Processing Temperature	210 - 230 °C	410 - 446 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China