

## Techmer ES Elastoblend® PA6 GF30 IM BK 30% Glass Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, 30% Glass Fiber Filled , Nylon 6, Heat Stabilized , Nylon 6, Impact Grade

### Material Notes:

Availability: North America  
Forms: Pellets  
Filler/Reinforcement: Glass Fiber Reinforcement, 30% Filler by Weight  
Additive: Heat Stabilizer, Impact Modifier and Lubricant  
Features: Heat Stabilized, Impact Modified and Lubricated  
Appearance: Black  
Information provided by TP Composites, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Techmer-ES-Elastoblend-PA6-GF30-IM-BK-30-Glass-Filled.php](http://www.lookpolymers.com/polymer_Techmer-ES-Elastoblend-PA6-GF30-IM-BK-30-Glass-Filled.php)

Physical Properties	Metric	English	Comments
Density	1.34 g/cc	0.0484 lb/in <sup>3</sup>	ASTM D792
Water Absorption	1.5 %	1.5 %	ASTM D570
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Flow	0.0035 cm/cm	0.0035 in/in	ASTM D955
	@Thickness 3.17 mm	@Thickness 0.125 in	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	120	120	ASTM D785
Tensile Strength, Yield	152 MPa	22100 psi	ASTM D638
Elongation at Break	4.0 %	4.0 %	ASTM D638
Flexural Strength	234 MPa	34000 psi	ASTM D790
Flexural Modulus	8.27 GPa	1200 ksi	ASTM D790
Izod Impact, Notched	1.01 J/cm	1.90 ft-lb/in	ASTM D256
	@Thickness 3.17 mm, Temperature -40.0 °C	@Thickness 0.125 in, Temperature -40.0 °F	
Izod Impact, Unnotched	2.03 J/cm	3.80 ft-lb/in	ASTM D256
	@Thickness 3.17 mm, Temperature 22.8 °C	@Thickness 0.125 in, Temperature 73.0 °F	
Izod Impact, Unnotched	13.9 J/cm	26.0 ft-lb/in	ASTM D256
	@Thickness 3.17 mm	@Thickness 0.125 in	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	36.0 µm/m-°C	20.0 µin/in-°F	ASTM D696
Deflection Temperature at 1.8 MPa			

(264 psi) Thermal Properties	210 Å°C Metric	410 Å°F English	Unannealed; ASTM D648 Comments
Flammability, UL94	HB  @Thickness 1.50 mm	HB  @Thickness 0.0591 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	2.00e+13 ohm-cm	2.00e+13 ohm-cm	ASTM D257
Dielectric Strength	15.4 kV/mm	390 kV/in	Method A (Short-Time); ASTM D149

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China