

Techmer ES Elastoblend® PA6 IM 511 HS L

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, Heat Stabilized , Nylon 6, Impact Grade

Material Notes:

Availability: North America
Forms: Pellets
Additive: Heat Stabilizer, Impact Modifier and Lubricant
Features: Heat Stabilized, Impact Modified and Lubricated
Uses: Low Temperature Applications
Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-Elastoblend-PA6-IM-511-HS-L.php

Physical Properties	Metric	English	Comments
Density	1.07 g/cc	0.0387 lb/in ³	ASTM D792
Water Absorption	1.5 % @Time 86400 sec	1.5 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0090 cm/cm @Thickness 3.17 mm	0.0090 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	70	70	ASTM D785
Tensile Strength, Yield	51.7 MPa	7500 psi	ASTM D638
Elongation at Break	150 %	150 %	ASTM D638
Flexural Strength	58.6 MPa	8500 psi	ASTM D790
Flexural Modulus	1.59 GPa	230 ksi	ASTM D790
Izod Impact, Notched	NB @Thickness 3.17 mm	NB @Thickness 0.125 in	ASTM D256
	NB @Thickness 3.17 mm, Temperature -40.0 °C	NB @Thickness 0.125 in, Temperature -40.0 °F	ASTM D256
Izod Impact, Unnotched	NB @Thickness 3.17 mm	NB @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	27.0 Åµm/m-Å°C	15.0 Åµin/in-Å°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	166 Å°C	330 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa	71.1 Å°C	160 Å°F	

<small>(264 psi)</small> Thermal Properties	Metric	English	Unannealed; ASTM D648 Comments
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Volume Resistivity	2.00e+13 ohm-cm	2.00e+13 ohm-cm	ASTM D257
Dielectric Strength	16.5 kV/mm	420 kV/in	Method A (Short-Time); ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China