

## Techmer ES Elastoblend® PA6 IM L W N

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Impact Grade

### Material Notes:

Availability: North America Forms: Pellets Additive: Impact Modifier and Lubricant Features: Impact Modified and Lubricated Appearance: Natural Color Information provided by TP Composites, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Techmer-ES-Elastoblend-PA6-IM-L-W-N.php](http://www.lookpolymers.com/polymer_Techmer-ES-Elastoblend-PA6-IM-L-W-N.php)

Physical Properties	Metric	English	Comments
Density	1.06 g/cc	0.0383 lb/in <sup>3</sup>	ASTM D792
Water Absorption	1.5 % @Time 86400 sec	1.5 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.015 cm/cm @Thickness 3.17 mm	0.015 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	105	105	ASTM D785
Tensile Strength, Yield	50.3 MPa	7300 psi	ASTM D638
Elongation at Break	200 %	200 %	ASTM D638
Flexural Strength	65.5 MPa	9500 psi	ASTM D790
Flexural Modulus	1.93 GPa	280 ksi	ASTM D790
Izod Impact, Notched	8.54 J/cm @Thickness 3.17 mm	16.0 ft-lb/in @Thickness 0.125 in	ASTM D256
Izod Impact, Unnotched	NB @Thickness 3.17 mm	NB @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	99.0 Åµm/m-Å°C	55.0 Åµin/in-Å°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	177 Å°C	350 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	60.0 Å°C	140 Å°F	Unannealed; ASTM D648
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Volume Resistivity	2.00e+13 ohm-cm	2.00e+13 ohm-cm	ASTM D257
Dielectric Strength	16.5 kV/mm	420 kV/in	Method A (Short-Time); ASTM D149

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China