

## Techmer ES Elastoblend® PA6/6 GF13 IM HS L 13% Glass Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 10% Glass Fiber Filled , Nylon 66, Glass Reinforced, Impact Grade , Nylon 66, Heat Stabilized

### Material Notes:

Availability: North America Forms: Pellets Filler/Reinforcement: Glass Fiber Reinforcement, 13% Filler by Weight Additive: Heat Stabilizer and Impact Modifier Features: Heat Stabilized and Impact Modified Processing Method: Injection Molding Information provided by TP Composites, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Techmer-ES-Elastoblend-PA66-GF13-IM-HS-L-13-Glass-Filled.php](http://www.lookpolymers.com/polymer_Techmer-ES-Elastoblend-PA66-GF13-IM-HS-L-13-Glass-Filled.php)

Physical Properties	Metric	English	Comments
Density	1.17 g/cc	0.0423 lb/in <sup>3</sup>	ASTM D792
Water Absorption	0.80 % @Time 86400 sec	0.80 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0060 cm/cm @Thickness 3.17 mm	0.0060 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	111	111	ASTM D785
Tensile Strength, Yield	91.0 MPa	13200 psi	ASTM D638
Elongation at Break	4.0 %	4.0 %	ASTM D638
Flexural Strength	110 MPa	16000 psi	ASTM D790
Flexural Modulus	36.2 GPa	5250 ksi	ASTM D790
Izod Impact, Notched	1.07 J/cm @Thickness 3.17 mm, Temperature -40.0 Å°C	2.00 ft-lb/in @Thickness 0.125 in, Temperature -40.0 Å°F	ASTM D256
	1.60 J/cm @Thickness 3.17 mm, Temperature 22.8 Å°C	3.00 ft-lb/in @Thickness 0.125 in, Temperature 73.0 Å°F	ASTM D256
Izod Impact, Unnotched	NB @Thickness 3.17 mm	NB @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	54.0 Åµm/m-Å°C	30.0 Åµin/in-Å°F	ASTM D696

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (264 psi)	252 Â°C	485 Â°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	220 Â°C	428 Â°F	Unannealed; ASTM D648
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+14 ohm-cm	1.00e+14 ohm-cm	ASTM D257
Dielectric Strength	19.3 kV/mm	490 kV/in	Method A (Short-Time); ASTM D149

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China