

## Techmer ES Elastoblend® PA6/ABS 1120 B1

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS)/Nylon Blend , Nylon

### Material Notes:

Availability: North America Forms: Pellets Additive: Impact Modifier Features: Impact Modified Processing Method: Injection

Molding Information provided by TP Composites, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Techmer-ES-Elastoblend-PA6ABS-1120-B1.php](http://www.lookpolymers.com/polymer_Techmer-ES-Elastoblend-PA6ABS-1120-B1.php)

Physical Properties	Metric	English	Comments
Density	1.06 g/cc	0.0383 lb/in <sup>3</sup>	ASTM D792
Water Absorption	1.5 % @Time 86400 sec	1.5 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0090 cm/cm @Thickness 3.17 mm	0.0090 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	105	105	ASTM D785
Tensile Strength	41.4 MPa	6000 psi	ASTM D638
Elongation at Yield	110 %	110 %	ASTM D638
Flexural Yield Strength	65.5 MPa	9500 psi	ASTM D790
Flexural Modulus	2.07 GPa	300 ksi	ASTM D790
Izod Impact, Notched	7.47 J/cm @Thickness 3.17 mm	14.0 ft-lb/in @Thickness 0.125 in	ASTM D256
Izod Impact, Unnotched	NB @Thickness 3.17 mm	NB @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	99.0 Åµm/m-Å°C	55.0 Åµin/in-Å°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	166 Å°C	330 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	51.7 Å°C	125 Å°F	Unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Volume Resistivity Electrical Properties	2.00e+13 ohm-cm Metric	2.00e+13 ohm-cm English	ASTM D257 Comments
Dielectric Strength	16.5 kV/mm	420 kV/in	Method A (Short-Time); ASTM D149

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China