

Techmer ES Electrablend® ABS 03011 FR BK MB 15% Stainless Steel Filled

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Stainless Steel Fiber Filled

Material Notes:

Availability: North America
Forms: Pellets
Filler/Reinforcement: Stainless Steel Fiber, 15% Filler by Weight
Features: Flame Retardant and Electromagnetic Shielding (EMI)
Appearance: Black
TPCI# 7965121
Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-Electrablend-ABS-03011-FR-BK-MB-15-Stainless-Steel-Filled.php

Physical Properties	Metric	English	Comments
Density	1.33 g/cc	0.0480 lb/in ³	ASTM D792
Water Absorption	0.30 % @Time 86400 sec	0.30 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0060 cm/cm @Thickness 3.17 mm	0.0060 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	47.6 MPa	6900 psi	ASTM D638
Elongation at Break	2.0 %	2.0 %	ASTM D638
Flexural Strength	81.4 MPa	11800 psi	ASTM D790
Flexural Modulus	6.21 GPa	900 ksi	ASTM D790
Izod Impact, Notched	0.374 J/cm @Thickness 3.17 mm	0.700 ft-lb/in @Thickness 0.125 in	ASTM D256
Izod Impact, Unnotched	1.60 J/cm @Thickness 3.17 mm	3.00 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	141 °C	285 °F	Unannealed; ASTM D648
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.0 - 1000 ohm-cm	1.0 - 1000 ohm-cm	ASTM D257
Surface Resistance	1.0 - 1000 ohm	1.0 - 1000 ohm	ASTM D257

Static Decay Electrical Properties	≤ 0.10 sec Metric	≤ 0.10 sec English	FTMS 101B Comments
Shielding Effectiveness	55 dB @Frequency 3.00e+7 - 1.00e+9 Hz	55 dB @Frequency 3.00e+7 - 1.00e+9 Hz	ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China