

## Techmer ES Electrablend® ABS 04002 BK 16% Stainless Steel Filled

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Stainless Steel Fiber Filled

### Material Notes:

Availability: North America  
Forms: Pellets  
Filler/Reinforcement: Stainless Steel Fiber, 16% Filler by Weight  
Features: Flame Retardant and Electromagnetic Shielding (EMI)  
Appearance: Black  
TPCI# 7965121  
Information provided by TP Composites, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Techmer-ES-Electrablend-ABS-04002-BK-16-Stainless-Steel-Filled.php](http://www.lookpolymers.com/polymer_Techmer-ES-Electrablend-ABS-04002-BK-16-Stainless-Steel-Filled.php)

Physical Properties	Metric	English	Comments
Density	1.33 g/cc	0.0480 lb/in <sup>3</sup>	ASTM D792
Water Absorption	0.30 % @Time 86400 sec	0.30 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0060 cm/cm @Thickness 3.17 mm	0.0060 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	47.6 MPa	6900 psi	ASTM D638
Elongation at Break	2.0 %	2.0 %	ASTM D638
Flexural Strength	81.4 MPa	11800 psi	ASTM D790
Flexural Modulus	6.21 GPa	900 ksi	ASTM D790
Izod Impact, Notched	0.374 J/cm @Thickness 3.17 mm	0.700 ft-lb/in @Thickness 0.125 in	ASTM D256
Izod Impact, Unnotched	1.60 J/cm @Thickness 3.17 mm	3.00 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	141 °C	285 °F	Unannealed; ASTM D648
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.0 - 1000 ohm-cm	1.0 - 1000 ohm-cm	ASTM D257
Surface Resistance	1.0 - 1000 ohm	1.0 - 1000 ohm	ASTM D257

Static Decay Electrical Properties	$\leq 0.10$ sec Metric	$\leq 0.10$ sec English	FTMS 101B Comments
Shielding Effectiveness	55 dB	55 dB	ASTM D4935

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China