

## Techmer ES Electrablend® PA6 GF20 20% Glass Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 20% Glass Fiber Filled

### Material Notes:

Availability: North America Forms: Pellets Filler/Reinforcement: Glass Fiber Reinforcement, 20% Filler by Weight/Unspecified

Filler/Reinfor.Additive: Lubricant Features: Conductive and Lubricated Appearance: Black Information provided by TP Composites, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Techmer-ES-Electrablend-PA6-GF20-20-Glass-Filled.php](http://www.lookpolymers.com/polymer_Techmer-ES-Electrablend-PA6-GF20-20-Glass-Filled.php)

Physical Properties	Metric	English	Comments
Density	1.39 g/cc	0.0502 lb/in <sup>3</sup>	ASTM D792
Water Absorption	0.80 % @Time 86400 sec	0.80 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0070 cm/cm @Thickness 3.17 mm	0.0070 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	117	117	ASTM D785
Tensile Strength, Yield	117 MPa	17000 psi	ASTM D638
Elongation at Break	3.5 %	3.5 %	ASTM D638
Flexural Strength	190 MPa	27500 psi	ASTM D790
Flexural Modulus	8.27 GPa	1200 ksi	ASTM D790
Izod Impact, Notched	0.534 J/cm @Thickness 3.17 mm	1.00 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	57.6 Åµm/m-Å°C	32.0 Åµin/in-Å°F	ASTM D696
Deflection Temperature at 1.8 MPa (264 psi)	210 Å°C	410 Å°F	Unannealed; ASTM D648
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Volume Resistivity	10000 - 1.00e+7 ohm-cm	10000 - 1.00e+7 ohm-cm	ASTM D257
Surface Resistance	100 ohm - 1e+05	100 ohm - 1e+05	ASTM D257

Electrical Properties

Metric

English

Comments

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China