

Techmer ES Electrablend® PC SS15 FR BK 15% Stainless Steel Filled

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, Stainless Steel Fiber

Material Notes:

Availability: North America Forms: Pellets Filler/Reinforcement: Stainless Steel Fiber, 15% Filler by Weight Features: Electromagnetic Shielding (EMI) and Flame Retardant Appearance: Black Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-Electrablend-PC-SS15-FR-BK-15-Stainless-Steel-Filled.php

| Physical Properties | Metric | English | Comments |
|-----------------------------|------------------------------------|-------------------------------------|-----------|
| Density | 1.32 g/cc | 0.0477 lb/in ³ | ASTM D792 |
| Water Absorption | 0.10 % @Time 86400 sec | 0.10 % @Time 24.0 hour | ASTM D570 |
| Linear Mold Shrinkage, Flow | 0.0020 cm/cm @Thickness 3.17 mm | 0.0020 in/in @Thickness 0.125 in | ASTM D955 |

| Mechanical Properties | Metric | English | Comments |
|-------------------------|----------------------------------|--------------------------------------|-----------|
| Tensile Strength, Yield | 90.3 MPa | 13100 psi | ASTM D638 |
| Elongation at Break | 3.0 % | 3.0 % | ASTM D638 |
| Flexural Yield Strength | 137 MPa | 19900 psi | ASTM D790 |
| Flexural Modulus | 5.65 GPa | 820 ksi | ASTM D790 |
| Izod Impact, Notched | 0.961 J/cm @Thickness 3.17 mm | 1.80 ft-lb/in @Thickness 0.125 in | ASTM D256 |
| Izod Impact, Unnotched | 4.27 J/cm @Thickness 3.17 mm | 8.00 ft-lb/in @Thickness 0.125 in | ASTM D256 |

| Thermal Properties | Metric | English | Comments |
|---|---------------------------|-----------------------------|-----------------------|
| Deflection Temperature at 1.8 MPa (264 psi) | 141 °C | 285 °F | Unannealed; ASTM D648 |
| Flammability, UL94 | V-0 @Thickness 1.50 mm | V-0 @Thickness 0.0590 in | |

| Electrical Properties | Metric | English | Comments |
|-----------------------|-------------|-------------|-----------|
| Volume Resistivity | 1000 ohm-cm | 1000 ohm-cm | ASTM D257 |
| Surface Resistance | 1000 ohm | 1000 ohm | ASTM D257 |

| Electrical Properties | Metric | English | Comments |
|-------------------------|-----------------|-----------------|------------|
| Static Decay | ≤ 0.10 sec | ≤ 0.10 sec | FTMS 101B |
| Shielding Effectiveness | 55 dB | 55 dB | ASTM D4935 |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China