

## Techmer ES Electrablend® POM C BK Acetal

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Copolymer, Unreinforced

### Material Notes:

Availability: North America Forms: Pellets Filler/Reinforcement: Unspecified Filler/Reinfor. Features: Conductive and Copolymer Appearance: Black Information provided by TP Composites, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Techmer-ES-Electrablend-POM-C-BK-Acetal.php](http://www.lookpolymers.com/polymer_Techmer-ES-Electrablend-POM-C-BK-Acetal.php)

Physical Properties	Metric	English	Comments
Density	1.37 g/cc	0.0495 lb/in <sup>3</sup>	ASTM D792
Water Absorption	0.30 % @Time 86400 sec	0.30 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.021 cm/cm @Thickness 3.17 mm	0.021 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	100	100	ASTM D785
Tensile Strength, Yield	41.4 MPa	6000 psi	ASTM D638
Elongation at Break	30 %	30 %	ASTM D638
Flexural Strength	55.2 MPa	8000 psi	ASTM D790
Flexural Modulus	2.07 GPa	300 ksi	ASTM D790
Izod Impact, Notched	0.534 J/cm @Thickness 3.17 mm	1.00 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	72.0 Åµm/m-Å°C	40.0 Åµin/in-Å°F	ASTM D696
Deflection Temperature at 1.8 MPa (264 psi)	76.7 Å°C	170 Å°F	Unannealed; ASTM D648
Flammability, UL94	HB @Thickness 1.50 mm	HB @Thickness 0.0591 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	100 ohm-cm - 1e+05	100 ohm-cm - 1e+05	ASTM D257

Surface Resistance Electrical Properties	1e+05 - 1.00e+9 ohm Metric	1e+05 - 1.00e+9 ohm English	ASTM D257 Comments
---	-------------------------------	--------------------------------	-----------------------

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China