

Techmer ES HiFill[®] ABS HI 0230 High Impact

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Impact Grade, Molded

Material Notes:

Availability: North America Forms: Pellets Filler/Reinforcement: Unspecified Filler/Reinfor Features: High Density and High Impact

Resistance Processing Method: Injection Molding Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-ABS-HI-0230-High-Impact.php

Physical Properties	Metric	English	Comments
Density	2.30 g/cc	0.0831 lb/in ³	ASTM D792
Water Absorption	0.19 % @Time 86400 sec	0.19 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0030 cm/cm @Thickness 3.17 mm	0.0030 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength	55.8 MPa	8100 psi	ASTM D638
Elongation at Yield	2.0 %	2.0 %	ASTM D638
Flexural Yield Strength	103 MPa	15000 psi	ASTM D790
Flexural Modulus	9.65 GPa	1400 ksi	ASTM D790
Izod Impact, Notched	0.587 J/cm @Thickness 3.17 mm	1.10 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	98.9 Å°C	210 Å°F	Unannealed; ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China