

Techmer ES HiFill FR[®] ABS FR V2 BK

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Unreinforced, Flame Retardant

Material Notes:

Availability: North America Forms: Pellets Features: Flame Retardant Appearance: Black Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-FR-ABS-FR-V2-BK.php

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in ³	ASTM D792
Water Absorption	0.30 %	0.30 %	ASTM D570
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Flow	0.0040 cm/cm	0.0040 in/in	ASTM D955
	@Thickness 3.17 mm	@Thickness 0.125 in	
Melt Flow	5.0 g/10 min	5.0 g/10 min	ASTM D1238
	@Load 3.80 kg, Temperature 230 Â°C	@Load 8.38 lb, Temperature 446 Â°F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	100	100	ASTM D785
Tensile Strength, Yield	40.7 MPa	5900 psi	ASTM D638
Elongation at Break	3.1 %	3.1 %	ASTM D638
Flexural Strength	71.0 MPa	10300 psi	ASTM D790
Flexural Modulus	2.34 GPa	340 ksi	ASTM D790
Izod Impact, Notched	2.14 J/cm	4.00 ft-lb/in	ASTM D256
	@Thickness 3.17 mm	@Thickness 0.125 in	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	93.9 Â°C	201 Â°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	81.1 Â°C	178 Â°F	Unannealed; ASTM D648
Flammability, UL94	V-2	V-2	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China