

Techmer ES HiFill FR® HDPE FR-HB

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE

Material Notes:

Availability: North America Forms: Pellets Features: Flame Retardant Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-FR-HDPE-FR-HB.php

Physical Properties	Metric	English	Comments
Density	1.02 g/cc	0.0368 lb/in ³	ASTM D792
Water Absorption	0.020 % @Time 86400 sec	0.020 % @Time 24.0 hour	ASTM D570
Melt Flow	8.0 g/10 min @Load 2.16 kg, Temperature 190 °C	8.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	26.9 MPa	3900 psi	ASTM D638
Elongation at Break	200 %	200 %	ASTM D638
Flexural Strength	35.2 MPa	5100 psi	ASTM D790
Flexural Modulus	8.27 GPa	1200 ksi	ASTM D790
Izod Impact, Notched	0.747 J/cm @Thickness 3.17 mm	1.40 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Flammability, UL94	HB	HB	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China