

Techmer ES HiFill FR[®] PA4/6 GF30 FR HS X 30% Glass Filled (Conditioned)

Category : Polymer , Thermoplastic , Nylon , Nylon 46 , Nylon 46, Flame Retarded + Glass Fiber Reinforced

Material Notes:

Availability: North America Forms: Pellets Filler/Reinforcement: Glass Fiber Reinforcement, 30% Filler by Weight Additive: Heat Stabilizer

Features: Flame Retardant and Heat Stabilized UL File Number: E157318 Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-FR-PA46-GF30-FR-HS-X-30-Glass-Filled-Conditioned.php

Physical Properties	Metric	English	Comments
Density	1.68 g/cc	0.0607 lb/in ³	ASTM D792
Water Absorption	0.90 % @Time 86400 sec	0.90 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0050 cm/cm @Thickness 3.17 mm	0.0050 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	100	100	ASTM D785
Tensile Strength, Yield	124 MPa	18000 psi	ASTM D638
Elongation at Yield	3.8 %	3.8 %	ASTM D638
Flexural Yield Strength	190 MPa	27600 psi	ASTM D790
Flexural Modulus	8.27 GPa	1200 ksi	ASTM D790
Izod Impact, Notched	1.01 J/cm @Thickness 3.17 mm	1.90 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	36.0 Åµm/m-Å°C	20.0 Åµin/in-Å°F	ASTM D696
Deflection Temperature at 1.8 MPa (264 psi)	123 Å°C	254 Å°F	Unannealed; ASTM D648
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+10 ohm-cm	1.00e+10 ohm-cm	ASTM D257
Dielectric Strength	24.0 kV/mm	610 kV/in	Method A (Short-Time); ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China