

Techmer ES HiFill FR[®] PA6 FR-N HS

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Heat Stabilized , Nylon 6 , Unreinforced , Flame Retardant

Material Notes:

Availability: North America
Forms: Pellets
Additive: Heat Stabilizer and Lubricant
Features: Flame Retardant, Heat Stabilized and Lubricated
Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-FR-PA6-FR-N-HS.php

Physical Properties	Metric	English	Comments
Density	1.19 g/cc	0.0430 lb/in ³	ASTM D792
Water Absorption	0.70 % @Time 86400 sec	0.70 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.012 cm/cm @Thickness 3.17 mm	0.012 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	112	112	ASTM D785
Tensile Strength, Yield	65.5 MPa	9500 psi	ASTM D638
Elongation at Break	20 %	20 %	ASTM D638
Flexural Modulus	2.00 GPa	290 ksi	ASTM D790
Izod Impact, Notched	0.481 J/cm @Thickness 3.17 mm	0.900 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	59.4 Åµm/m-Å°C	33.0 Åµin/in-Å°F	ASTM D696
Deflection Temperature at 1.8 MPa (264 psi)	60.0 Å°C	140 Å°F	Unannealed; ASTM D648
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+14 ohm-cm	1.00e+14 ohm-cm	ASTM D257
Surface Resistance	1.00e+12 ohm	1.00e+12 ohm	ASTM D257
Dielectric Strength	20.9 kV/mm	530 kV/in	Method A (Short-Time); ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China