

Techmer ES HiFill FR[®] PA6 GF33 FR HS L GY300 33% Glass Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 30% Glass Fiber Filled , Nylon 6 , Heat Stabilized

Material Notes:

Availability: North America
Forms: Pellets
Filler/Reinforcement: Glass Fiber Reinforcement, 33% Filler by Weight
Additive: Heat Stabilizer, UV Stabilizer and Lubricant
Features: Flame Retardant, Heat Stabilized, Good UV Resistance and Lubricated Appearance: Grey
Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-FR-PA6-GF33-FR-HS-L-GY300-33-Glass-Filled.php

Physical Properties	Metric	English	Comments
Density	1.63 g/cc	0.0589 lb/in ³	ASTM D792
Water Absorption	0.75 %	0.75 %	ASTM D570
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Flow	0.0030 cm/cm	0.0030 in/in	ASTM D955
	@Thickness 3.17 mm	@Thickness 0.125 in	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	122	122	ASTM D785
Tensile Strength, Yield	149 MPa	21600 psi	ASTM D638
Elongation at Break	3.1 %	3.1 %	ASTM D638
Flexural Strength	193 MPa	28000 psi	ASTM D790
Flexural Modulus	8.96 GPa	1300 ksi	ASTM D790
Izod Impact, Notched	0.747 J/cm	1.40 ft-lb/in	ASTM D256
	@Thickness 3.17 mm	@Thickness 0.125 in	
Izod Impact, Unnotched	8.54 J/cm	16.0 ft-lb/in	ASTM D256
	@Thickness 3.17 mm	@Thickness 0.125 in	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	21.6 Åµm/m-Å°C	12.0 Åµin/in-Å°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	218 Å°C	425 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	216 Å°C	420 Å°F	Unannealed; ASTM D648
UL RTI, Electrical	120 Å°C	248 Å°F	UL 746

Thermal Properties	Metric	English	Comments
UL RTI, Mechanical without Impact	115 Â°C	239 Â°F	UL746
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+14 ohm-cm	1.00e+14 ohm-cm	ASTM D257
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	ASTM D257
Dielectric Strength	16.1 kV/mm	410 kV/in	Method A (Short-Time); ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China