

## Techmer ES HiFill FR® PA6/6 GF30 FR HS L 30% Glass Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Glass Fiber Filled , Nylon 66, Heat Stabilized

### Material Notes:

Availability: North America  
Forms: Pellets  
Filler/Reinforcement: Glass Fiber, 30% Filler by Weight  
Additive: Heat Stabilizer and Lubricant  
Features: Flame Retardant, Lubricated and Heat Stabilized  
Information provided by TP Composites, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Techmer-ES-HiFill-FR-PA66-GF30-FR-HS-L-30-Glass-Filled.php](http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-FR-PA66-GF30-FR-HS-L-30-Glass-Filled.php)

Physical Properties	Metric	English	Comments
Density	1.67 g/cc	0.0603 lb/in <sup>3</sup>	ASTM D792
Water Absorption	0.70 % @Time 86400 sec	0.70 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0030 cm/cm @Thickness 3.17 mm	0.0030 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	119	119	ASTM D785
Tensile Strength, Yield	162 MPa	23500 psi	ASTM D638
Elongation at Break	3.0 %	3.0 %	ASTM D638
Flexural Strength	228 MPa	33000 psi	ASTM D790
Flexural Modulus	10.7 GPa	1550 ksi	ASTM D790
Izod Impact, Notched	1.23 J/cm @Thickness 3.17 mm	2.30 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	34.2 µm/m-°C	19.0 µin/in-°F	ASTM D696
Deflection Temperature at 1.8 MPa (264 psi)	250 °C	482 °F	Unannealed; ASTM D648
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+14 ohm-cm	1.00e+14 ohm-cm	ASTM D257
Surface Resistance	1.00e+12 ohm	1.00e+12 ohm	ASTM D257

Dielectric Strength Electrical Properties	17.7 kV/mm Metric	450 kV/in English	Method A (Short-Time); ASTM D149 Comments
--	----------------------	----------------------	--

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China