

Techmer ES HiFill® HIPS TM40 WT 40% Talc Filled

Category : Polymer , Thermoplastic , Polystyrene (PS) , Polystyrene, Impact Modified

Material Notes:

Availability: North America Forms: Pellets Filler/Reinforcement: Talc Filler, 40% Filler by Weight Appearance: White Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-HIPS-TM40-WT-40-Talc-Filled.php

Physical Properties	Metric	English	Comments
Density	1.22 g/cc	0.0441 lb/in ³	ASTM D792
Melt Flow	6.0 g/10 min @Load 5.00 kg, Temperature 200 °C	6.0 g/10 min @Load 11.0 lb, Temperature 392 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	22.8 MPa	3300 psi	ASTM D638
Elongation at Break	10 %	10 %	ASTM D638
Flexural Strength	35.9 MPa	5200 psi	ASTM D790
Flexural Modulus	2.00 GPa	290 ksi	ASTM D790
Izod Impact, Notched	1.07 J/cm @Thickness 3.17 mm	2.00 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	7.20 µm/m-°C	4.00 µin/in-°F	ASTM D696
Deflection Temperature at 1.8 MPa (264 psi)	80.0 °C	176 °F	Unannealed; ASTM D648
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+13 ohm-cm	1.00e+13 ohm-cm	ASTM D257
Dielectric Strength	18.1 kV/mm	460 kV/in	Method A (Short-Time); ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China