

Techmer ES HiFill[®] PA12 L N MB

Category : Polymer , Thermoplastic , Nylon , Nylon 12

Material Notes:

Availability: North America Forms: Pellets Features: Low Viscosity TPCI# 8807105 Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-PA12-L-N-MB.php

Physical Properties	Metric	English	Comments
Density	1.02 g/cc	0.0368 lb/in ³	ASTM D792
Water Absorption	0.70 %	0.70 %	ASTM D570
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Flow	0.016 cm/cm	0.016 in/in	ASTM D955
	@Thickness 3.17 mm	@Thickness 0.125 in	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	106	106	ASTM D785
Tensile Strength, Yield	65.5 MPa	9500 psi	ASTM D638
Elongation at Break	20 %	20 %	ASTM D638
Flexural Strength	75.8 MPa	11000 psi	ASTM D790
Flexural Modulus	1.72 GPa	250 ksi	ASTM D790
Izod Impact, Notched	0.374 J/cm	0.700 ft-lb/in	ASTM D256
	@Thickness 3.17 mm	@Thickness 0.125 in	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	126 $\mu\text{m/m-}^\circ\text{C}$	70.0 $\mu\text{in/in-}^\circ\text{F}$	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	132 $^\circ\text{C}$	270 $^\circ\text{F}$	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	77.8 $^\circ\text{C}$	172 $^\circ\text{F}$	Unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+11 ohm-cm	1.00e+11 ohm-cm	ASTM D257
Dielectric Strength	25.6 kV/mm	650 kV/in	Method A (Short-Time); ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China