

Techmer ES HiFill[®] PA4/6 HS LBK

Category : Polymer , Thermoplastic , Nylon , Nylon 46 , Nylon 46, Unreinforced , Nylon 6 , Nylon 6, Heat Stabilized

Material Notes:

Availability: North America
Forms: Pellets
Additive: Heat Stabilizer and Lubricant
Features: Heat Stabilized and Lubricated
Appearance: Black
TPCI# 9651150
Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-PA46-HS-LBK.php

Physical Properties	Metric	English	Comments
Density	1.18 g/cc	0.0426 lb/in ³	ASTM D792
Water Absorption	2.3 %	2.3 %	ASTM D570
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Flow	0.018 cm/cm	0.018 in/in	ASTM D955
	@Thickness 3.17 mm	@Thickness 0.125 in	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	100	100	ASTM D785
Tensile Strength, Yield	100 MPa	14500 psi	ASTM D638
Elongation at Break	40 %	40 %	ASTM D638
Flexural Strength	103 MPa	15000 psi	ASTM D790
Flexural Modulus	3.00 GPa	435 ksi	ASTM D790
Izod Impact, Notched	0.747 J/cm	1.40 ft-lb/in	ASTM D256
	@Thickness 3.17 mm, Temperature -40.0 Â°C	@Thickness 0.125 in, Temperature -40.0 Â°F	
Izod Impact, Unnotched	0.801 J/cm	1.50 ft-lb/in	ASTM D256
	@Thickness 3.17 mm, Temperature 22.8 Â°C	@Thickness 0.125 in, Temperature 73.0 Â°F	
Izod Impact, Unnotched	NB	NB	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	90.0 Âµm/m-Â°C	50.0 Âµin/in-Â°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	221 Â°C	430 Â°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	160 Â°C	320 Â°F	Unannealed; ASTM D648

Thermal Properties	Metric	English	Comments
Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+14 ohm-cm	1.00e+14 ohm-cm	ASTM D257
Dielectric Strength	21.7 kV/mm	550 kV/in	Method A (Short-Time); ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China