

**Techmer ES HiFill<sup>®</sup> PA6 0266 B**

Category : Polymer , Thermoplastic , Nylon , Nylon 6

**Material Notes:**

Availability: North America  
 Forms: Pellets  
 Filler/Reinforcement: Unspecified Filler/Reinfor  
 Features: High Specific Gravity  
 Information provided by TP Composites, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Techmer-ES-HiFill-PA6-0266-B.php](http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-PA6-0266-B.php)

Physical Properties	Metric	English	Comments
Density	2.66 g/cc	0.0961 lb/in <sup>3</sup>	ASTM D792
Water Absorption	0.10 % @Time 86400 sec	0.10 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0010 cm/cm @Thickness 3.17 mm	0.0010 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	44.8 MPa	6500 psi	ASTM D638
Elongation at Break	1.0 %	1.0 %	ASTM D638
Flexural Strength	48.3 MPa	7000 psi	ASTM D790
Flexural Modulus	6.89 GPa	1000 ksi	ASTM D790
Izod Impact, Notched	0.427 J/cm @Thickness 3.17 mm	0.800 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	174 Â°C	345 Â°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	167 Â°C	333 Â°F	Unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+13 - 1.00e+14 ohm-cm	1.00e+13 - 1.00e+14 ohm-cm	ASTM D257

**Contact Songhan Plastic Technology Co.,Ltd.**Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China