

Techmer ES HiFill[®] PA6 GF30 L N BK 30% Glass Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 30% Glass Fiber Filled

Material Notes:

Availability: North America
Forms: Pellets
Filler/Reinforcement: Glass Fiber Reinforcement, 30% Filler by Weight
Processing Method: Injection Molding
Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-PA6-GF30-L-N-BK-30-Glass-Filled.php

Physical Properties	Metric	English	Comments
Density	1.37 g/cc	0.0495 lb/in ³	ASTM D792
Water Absorption	1.3 % @Time 86400 sec	1.3 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0030 cm/cm @Thickness 3.17 mm	0.0030 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	118	118	ASTM D785
Tensile Strength, Yield	176 MPa	25500 psi	ASTM D638
Elongation at Break	2.4 %	2.4 %	ASTM D638
Flexural Strength	276 MPa	40000 psi	ASTM D790
Flexural Modulus	1.03 GPa	150 ksi	ASTM D790
Izod Impact, Notched	1.49 J/cm @Thickness 3.17 mm	2.80 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	16.2 Åµm/m-Å°C	9.00 Åµin/in-Å°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	216 Å°C	420 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	210 Å°C	410 Å°F	Unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	ASTM D257
Dielectric Strength	16.1 kV/mm	410 kV/in	Method A (Short-Time); ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China