

Techmer ES HiFill[®] PA6 GF33 L UV BK 33% Glass Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 30% Glass Fiber Filled

Material Notes:

Availability: North America
Forms: Pellets
Filler/Reinforcement: Glass Fiber Reinforcement, 33% Filler by Weight
Additive: Lubricant and UV Stabilizer
Features: Lubricated and Good UV Resistance
Appearance: Black
Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-PA6-GF33-L-UV-BK-33-Glass-Filled.php

Physical Properties	Metric	English	Comments
Density	1.38 g/cc	0.0499 lb/in ³	ASTM D792
Water Absorption	1.1 % @Time 86400 sec	1.1 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0030 cm/cm @Thickness 3.17 mm	0.0030 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	121	121	ASTM D785
Tensile Strength, Yield	165 MPa	24000 psi	ASTM D638
Elongation at Break	3.5 %	3.5 %	ASTM D638
Flexural Strength	263 MPa	38100 psi	ASTM D790
Flexural Modulus	8.62 GPa	1250 ksi	ASTM D790
Izod Impact, Notched	0.908 J/cm @Thickness 3.17 mm	1.70 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	37.8 Åm/m-Å°C	21.0 Åin/in-Å°F	ASTM D696
Melting Point	220 Å°C	428 Å°F	
Deflection Temperature at 0.46 MPa (66 psi)	216 Å°C	420 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	210 Å°C	410 Å°F	Unannealed; ASTM D648
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Electrical Properties	Metric 15 ohm-cm	English 5 ohm-cm	Comments
Dielectric Strength	16.5 kV/mm	420 kV/in	Method A (Short-Time); ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China