

## Techmer ES HiFill® PA6 GF50 IM L NAT002 50% Glass Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 50% Glass Fiber Filled

### Material Notes:

Availability: North America  
Forms: Pellets  
Filler/Reinforcement: Glass Fiber Reinforcement, 50% Filler by Weight  
Processing Method: Injection Molding  
Information provided by TP Composites, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Techmer-ES-HiFill-PA6-GF50-IM-L-NAT002-50-Glass-Filled.php](http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-PA6-GF50-IM-L-NAT002-50-Glass-Filled.php)

Physical Properties	Metric	English	Comments
Density	1.55 g/cc	0.0560 lb/in <sup>3</sup>	ASTM D792
Water Absorption	0.65 % @Time 86400 sec	0.65 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0022 cm/cm @Thickness 3.17 mm	0.0022 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	121	121	ASTM D785
Tensile Strength, Yield	172 MPa	25000 psi	ASTM D638
Elongation at Break	2.8 %	2.8 %	ASTM D638
Flexural Strength	310 MPa	45000 psi	ASTM D790
Flexural Modulus	9.31 GPa	1350 ksi	ASTM D790
Izod Impact, Notched	3.74 J/cm @Thickness 3.17 mm	7.00 ft-lb/in @Thickness 0.125 in	ASTM D256
Izod Impact, Unnotched	NB @Thickness 3.17 mm	NB @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	14.4 Åµm/m-Å°C	8.00 Åµin/in-Å°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	218 Å°C	425 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	213 Å°C	415 Å°F	Unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Volume Resistivity Electrical Properties	1.00e+15 ohm-cm Metric	1.00e+15 ohm-cm English	ASTM D257 Comments
Dielectric Strength	17.7 kV/mm	450 kV/in	Method A (Short-Time); ASTM D149

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China